

Product Name: White tile adhesive (Protile bond 2030W)

Description: Cementous tile adhesive with extended open time and reduced slip features

Technical data

Product code: CM2003	Item	Feature	Test method	Unit	Standard values	Typical result
Tile adhesive Protile bond 2030W	1	Color	visual	*	*	White
	2	Initial adhesion strength	INSO 12492-1	N/mm ²	≥ 0.5	0.81
	3	Adhesion strength after immersion in water	INSO 12492-1	N/mm ²	≥ 0.5	0.70
	4	Adhesion strength after heat ageing	INSO 12492-1	N/mm ²	≥ 0.5	0.62
	5	Adhesion strength after freeze-thaw cycles	INSO 12492-1	N/mm ²	≥ 0.5	0.61
	6	Open time adhesion strength after 30 minutes	INSO 12492-1	N/mm ²	≥ 0.5	0.72
	7	Slip	INSO 12492-1	mm	≤ 0.5	0.25

The given data is stated in standard conditions and can have changes in different workshop conditions and various type of substrate.

Tips, details, and features

- In accordance with the Iran national standard INSO 12942-1 in the C1TE class, and compatible with the international standard EN12004.
- A very suitable alternative to traditional mortars.
- Designed for tiling floors and walls in dry environments.
- Designed for gluing all types of common ceramic tiles with high water absorption rate and small to medium sizes.

Consumption rate

3-5 Kg per square meter. These values can vary according to the size of the teeth of the trowel and the type and dimensions of the tile. The amount of consumption is approximate and may change depending on the type of work surface.

All information based on technical knowledge and existing standards has been obtained and presented in standard environmental conditions. The policy and organizational strategy of Sepidgach Saveh Company is in line with the research and development and qualitative growth of products, and in this regard, the company reserves the right to change technical data at any time. In case of any changes in the technical specifications, the previously published data will be invalid and the new data will be provided to you through the company's website. Obviously, the commitment of this company is limited to the correct use of the product in suitable environmental conditions in accordance with published standards and guidelines. It should be noted that all the engineering technical knowledge, standards and methods of use are not included in this sheet and the executives are obliged to apply all the executive technical orders separately.